

## PRODUCT SPECIFICATION

GRADE ADBASE 2CST (GROUP II)

SPEC NO. 8222

PROPERTY	UNIT	LIMIT		TEST METHOD
		MIN	MAX	
APPEARANCE	-	CLEAR & BRIGHT		ASTM D4176-1
VISCOSITY, KINEMATIC AT 100°C	mm <sup>2</sup> /s	2.100	2.300	ASTM D445
VISCOSITY, KINEMATIC AT 40°C	mm <sup>2</sup> /s	REPORT		ASTM D445
VISCOSITY INDEX	-	REPORT		ASTM D2270
POUR POINT	°c	-	-27	ASTM D97 ASTM D5949 OR ASTM D5950
FLASH POINT (COC)	°c	155	-	ASTM D92
SULFUR	mg/kg	-	10	ASTM D2622 OR ASTM D7039
WATER CONTENT	mg/kg	-	50.0	ASTM D6304 OR ISO 12937
COLOR, SAYBOLT	-	REPORT		ASTM D156
DENSITY AT 15°C	g/ml	REPORT		ASTM D4052 OR ASTM D1298
COPPER STRIP CORROSION (3H/100 °C)	-	REPORT		ASTM D130
ACID NUMBER	mg KOH/g	REPORT		ASTM D664
MICRO METHOD CARBON RESIDUE	% (m/m)	REPORT		ASTM D524 ASTM D4530 OR ISO 4262
SATURATES	mass %	REPORT		ASTM D2007 ASTM D7419 OR IP 368
AROMATICS	mass %	REPORT		ASTM D2007 ASTM D7419 OR IP 368